


Size Effects on Dopant Activation in Si Fins

S. Folkersma^{a,b,1}, J. Bogdanowicz^a, P. Favia^a, L. Wouters^a, K. Paredis^a, A. Franquet^a, V. Spampinato^a, D. H. Petersen^c, O. Hansen^c, H. H. Henrichsen^d, P. F. Nielsen^d, L. Shiv^d and W. Vandervorst^{a,b}


^aIMEC, Kapeldreef 75, B-3000 Leuven, Belgium
^bInstituut voor Kern- en Stralingsfysika, KU Leuven, Celestijnenlaan 200D, B-3001 Leuven, Belgium
^cDepartment of Micro- and Nanotechnology, Technical University of Denmark, DTU Nanotech Building 345 East, DK-2800 Kgs. Lyngby, Denmark
^dCAPRES A/S, Scion-DTU, Building 373, DK-2800 Kgs. Lyngby, Denmark
¹email address: steven.folkersma@imec.be

I. Introduction

2D technology (MOSFET):




3D technology (finFET):




MicroHall-A300CAPRES

2. Micro-four point probe: from pads to fins

- Pads:** Technique is commonly used for measurements on blanket and on large pads ($> 20 \times 35 \mu\text{m}^2$).




- Fins:** Can be aligned to fins and measure fin resistance.




3. Measuring on dense fins

Additional challenge when fin pitch < electrode contact size:




- Electrical contact** between the μ 4PP electrodes and the fins is controlled such that only a single fin is contacted.
- Measured resistance** follows resistance estimated by model (see next box).




S. Folkersma, et al., Beilstein Jour. of Nanotech., vol. 9, 2018, pp. 1853-1857.

4. Size Dependent Dopant Activation

- Fin width dependent** sheet resistance (R_s) of B implanted Si fins as measured by μ 4pp.
- R_s of widest fins comparable to R_s of a large pad of the same material.




- Model explains increase in R_s due to **non-conductive amorphous silicon** present after **450 °C anneal**.




- Defective area present after **1150 °C laser anneal** has a **40 % increased resistivity** as estimated with the same model.

5. Carrier profiling using μ 4PP

- New approach** cycling ion-beam sputtering and μ 4pp to measure carrier profile.



- Measure $R_s(z)$ with μ 4pp** → calculate $\rho(z)$ → $N_A(z)$
- A Gaussian shaped, **40 % active** dopant profile is obtained.



S. Folkersma, et al., IIT 2018 Proceedings, to be published

Conclusions

- μ 4PP can be used to precisely ($\sigma < 2\%$) measure the fin sheet resistance of nm-wide Si fins.
- For the implanted and annealed Si fins, a **width-dependent sheet resistance** was measured and explained by non-conductive or less conductive areas along the top of the fin sidewalls.
- The **active dopant profile** in these fins is Gaussian shaped with a **40 % dopant activation**, as measured by μ 4PP.